



難燃バインダー

Clear FR-B / White FR-W

※受注生産品

1) 概要

Clear FR-B | White FR-W は、難燃性のバインダーです。カラーと架橋剤を添加してプリントするだけで、簡単に難燃性を付与することができます。

Clear FR-B | White FR-W は腐食性や発煙性が低いハロゲンフリーの難燃剤（ポリリン酸アンモニウム）を使用しており環境に配慮した商品です。ECO PASSPORT by OEKO-TEX®の認証を取得しています。

2) 性状

	Clear FR-B	White FR-W
外観	乳白色ペースト	白色ペースト
粘度 (mPa・s) (at 25°C)	70,000±10,000	90,000±10,000
pH	8.0±1.0	8.0±1.0

3) 使用方法

3) - 1 【処方】	クリアー	ホワイト
Clear FR-B	100	0
White FR-W	0	100
ネオカラー 各色	～8	～8
Fixer N	～2	～2
合計	～110	～110

4) 留意事項

- ・難燃性能は生地により異なりますので、事前テストを行ってください。
- ・御使用前によく攪拌してください。
- ・作業性の向上には乾燥遅効剤EGを2～3%を添加して下さい。
- ・インキ粘度を上げる場合は、エマコール R530E またはエマコール R600E を0.1～0.5%添加し均一に攪拌して下さい。
- ・インキ粘度を下げる場合は、触媒#3000を0.5～2.0%を添加して下さい。
- ・開封後は、密栓し冷暗所に保管下さい。

Recommended Parameters

Fabric Types



綿、T/C、
ポリエステル等

Screen Mesh



80～120mesh/inch

Squeegee



Durometer : 70/90/70
Square Edge

Flash & Cure



150° C×2-3min.

Pigment



Clear UP TO 8%

AUXILIARIES



Fixer N 2%

Storage



5° C—30° C

Clean Up



石鹼水又は湯



MATSUI SHIKISO CHEMICAL CO.,LTD.

64 Kamikazan Sakuradani-cho,
Yamashina-ku,
Kyoto 607-8466 Japan

☎ : 81-75-594-5612

☎ : 81-75-594-0829

✉ : export-sales@msc-color.co.jp

🌐 : www.msc-color.co.jp

The above information is based on our knowledges and experiences currently available. Please, test and evaluate before the actual use.